


Quality Registration Technical specification

QR 0022 Created: 08/07/2013

Technical specifications

CL60-CCL (Cable ladder Cover Clamp)



Finishing:	Stainless stee	Stainless steel 301							
Product	Number	Height	Width	Length	Dim A	Fmax	Unit	Packaging	
		(mm)	(mm)	(mm)	(mm)	(kN)		(unit)	
CL60-CCL-SS	10014	0	0	0			ST	50	

Mounting instructions:

-

Load capacity:

Standard: -

Max. load:

Load diagram: -

Information:

Coupler: -

Equipotential bonding: IEC61537

EC declaration: EC directive 2014/35/EU (Low voltage) as modified by directive 93/68/EEC (CE marking)

SS301

P. 1 / 3 Rev01: 05/10/2017



Quality Registration Technical specification

QR 0022 Created: 08/07/2013

Stainless steel (1.4310) AISI 301

Stainless steel is also known as inox steel or inox from the French inoxydable. The AISI 300 Series represents by far the largest group. The various types within this alloy group are derived from the traditional 18/8 composition (18% Cr/8% Ni). The structure even consists at ambient temperature, and sometimes far below, entirely of austenite, which is due to the presence of nickel in a ratio of about 8%. When it has reached a fully austenitic structure, the material is not ferromagnetic and offers good corrosion resistant.

Type 301 is a stainless steel with unusually high uniform elongation when correct composition balance and deformation conditions are achieved. It is suitable for extreme cold deformation. As a result of moderate to extreme cold deformation, its tensile strength increases significantly while retaining reasonable toughness. It is often used in the cold-rolled or cold-drawn state. Applications include counter tops, hubcaps, architecture and construction elements, high-strength springs, all kinds of clips, banisters, balustrades, etc.

Field of application according to resistance against corrosion:

Corrosion classes according EN ISO 12994

Corrosion	Atmospheric			
class	corrosion	Indoor environment	Outdoor environment	Surface treatments
C1	<0,1μm	Heated buildings with neutral atmospheres: offices, shops, schools, hotels.		Electro-galvanised (EG) EN ISO 2081
C2	0,1 - 0,7μm	Unheated buildings where condensation may occur: sports halls, warehouses, shops.	Rural areas. Atmosphere with low impurities.	Pre-galvanised (PG) EN 10327 – EN 10143
С3	0,7 - 2μm	Production facilities with high moisture levels and some air impurities due to industrial processes: production plants.	City and industrial atmosphere, some impurities, coastal areas with low salt loads.	Dipped-galvanised (DG) EN ISO 1461
C4	2 - 4µm	Production facilities with high moisture levels and high air impurities due to industrial processes: swimming pools, Chemical industry.	Industrial areas and coastal areas with low salt load.	Dipped-galvanised (DG) EN ISO 1461 Polyester coating (CO) EN ISO 12944
C5-I	4 - 8μm	Polyester coating (CO)	Industrial areas with high moisture level and aggressive atmosphere.	Duplex (DU) (Dipped galvanised + Polyester coating) Stainless steel AISI 316L
C5-M	4 - 8μm	EN ISO 12944	Coastal or offshore areas with salt load.	Duplex (DU) (Dipped galvanised + Polyester coating)

P. 2 / 3 Rev01: 05/10/2017



Quality Registration Technical specification

QR 0022 Created: 08/07/2013

Classification for resistance against corrosion according to IEC61537

Class	Reference- Material and Finish
0 (a)	None
1	Electroplated to a minimum thickness of 5 μm
2	Electroplated to a minimum thickness of 12 μm
3	Pre-galvanised to grade 275 to EN 10327 and EN 10326
4	Pre-galvanised to grade 350 to EN 10327 and EN 10326
5	Post-galvanised to a zinc mean coating thickness (minimum) of 45 μm according to ISO 1461 for zinc thickness only
6	Post-galvanised to a zinc mean coating thickness (minimum) of 55 μm according to ISO 1461 for zinc thickness only
7	Post-galvanised to a zinc mean coating thickness (minimum) of 70 μm according to ISO 1461 for zinc thickness only
8	Post-galvanised to a zinc mean coating thickness (minimum) of 85 μm according to ISO 1461 for zinc thickness only (usually high silicon steel)
9A	Stainless steel manufactured to ASTM: A 240/A 240M – 95a designation S30400 or EN 10088 grade 1-4301 without a post-treatment (b)
9B	Stainless steel manufactured to ASTM: A 240/A 240M – 95a designation S31603 or EN 10088 grade 1-4404 without a post-treatment (b)
9C	Stainless steel manufactured to ASTM: A 240/A 240M – 95a designation S30400 or EN 10088 grade 1-4301 with a post-treatment (b)
9D	Stainless steel manufactured to ASTM: A 240/A 240M – 95a designation S31603 or EN 10088 grade 1-4404 with a post-treatment (b)

⁽a) For materials which have no declared corrosion resistance classification.

P. 3 / 3 Rev01: 05/10/2017

 $_{(b)}$ The post-treatment process is used to improve the protection against crevice crack corrosion and the contamination by other steels.